

Pure and Natural Hydraulic Lime (NHL 3.5) Product Data

St Astier Natural Hydraulic Limes (NHL)

Conforms to European Norms EN 459 and BS 459
 Strength factor: 3.5 (Moderately hydraulic)
 Residue @ 0.09 mm: 6.5%
 Density (volumetric weight) : typical 650gr / litre
 Available (free) lime after slaking Ca(OH)_2 : 25% +
 Packing: 25kg. Bags

Contains no additives.
 Whiteness index: 72
 Surface cover (cm²pergram): 9000
 Expansion : < 1mm
 Residue of quick lime after slaking: < 1%
 Shelf life: 8-12 months kept sealed and dry

MORTARS MIX RATIO	Compressive strength N/mm ²			Elasticity Moduli (Mpa)			
	EN459*	1 : 2	1 : 2.5	1 : 3	1 : 2	1:2.5	1 :3
7 DAYS		0.75	0.57	0.53			
28 DAYS	3.5*	1.88	1.47	1.34	9010	9000	8070
6 MONTHS		7.1	5.34	3.94	15260	13501	13150
12 MONTHS		7.5	5.90	3.90	15280	13620	13150
24 MONTHS		8.63	6.00	3.97	17480	13785	13670
Consumption for 1m ³ of mortar Kg. +/- 10%		305	244	216			
EN 459/BS 459 (mortar ratio 1:1 by volume, with ISO 679 Sand)							

Mixing: can be mixed in cement mixers.

Application by spray gun: possible. Please consult us.

Working temperatures: not below 5°C or above 30°C. Make sure that high suction materials are thoroughly dampened before application. Avoid rapid drying due to high temperatures or strong winds by curing with a light water mist several times a day if necessary. See "Protecting Lime Mortar".

SUITABLE FOR LATH WORK / LIME CONCRETE/INJECTION/GROUTING See relevant sheets

Reworking: possible within 12 hours

Mortar composition: MASONRY/POINTING/ CAPPING/ BEDDING/ ASHLAR

Binder: sand ratio: from 1:1.5 to 1:3 depending on the support/background conditions, the size of the joint and the fineness of the sand. Always use well graded sands (3 - 4mm down to 75 microns).

See also "Applications & Good Working Practices Sands for Lime Mortars".

RENDERING

A. Scratch coat (3-5mm) 1 VOLUME OF NHL 3.5 : 1.5 VOLUMES OF SAND - Cast on

B. Undercoat (15-20mm) 1 VOLUME OF NHL 3.5 : 2 VOLUMES OF SAND*

C. Finishing (5-10mm) 1 VOLUME OF NHL 3.5 : 2.5 VOLUMES OF SAND

With very fine sands possibly containing clays the binder content may have to be reduced.

*At this dosage the consumption is approx. 0.35kg. of NHL 3.5 per m² for each mm thickness.

Please also refer to "Applications & Good Working Practices - NHL Renders".

For further Guidance, contact your St Astier Distributor.

Copyright © 2016 CESA, Chaux et Enduits de St Astier

